










L = Length of Pile



MAXIMUM PICKUP LENGTHS L

Type of Pick - Up	Prestressed 6" Oct.	Precast 8" or 10" Oct.	Prestressed 8" Sq.	Precast 10" Sq.
One - Point	52'	46'	59'	51'
Two - Point	75'	80'	67'	90'
Three - Point	105'	112'	93'	126'



* Number based on initial prestress force of $r_p \times$ Ultimate Tensile Stress, Prestress Losses, and min. 700 psi Unit Losses.
 $r_p = 0.75$ Low Relaxation
 $r_p = 0.70$ Stress - Relieved

PRESTRESSED PILE PROPERTIES

Gr. Code	Strand Diameter	* Number of Strands per Size "D"			Minimum Ultimate Tensile Strength Per Strand (lbs.)	Initial Prestressing Force Per Strand (lbs.)
		6" Oct.	8" Oct.	10" Oct.		
250	3/8"	11	13	16	27,000	18,900
	1/2"	8	10	12	36,000	25,200
270	3/8"	9	11	14	31,000	21,700
	1/2"	7	9	10	41,300	28,900
250	3/8"	9	11	13	27,000	20,200
	1/2"	7	8	10	36,000	27,000
270	3/8"	8	10	11	31,000	23,300
	1/2"	6	7	9	41,300	31,000

GENERAL NOTES

Construction Specifications : Arkansas State Highway and Transportation Department Standard Specifications for Highway Construction, (2003 edition), with applicable Supplemental Specifications and Special Provisions.
 Design Specification : ASHTO Standard Specifications for Highway Bridges (2002 edition), with current interim specifications.

Concrete : Concrete in the Precast Prestressed Piles shall be Class S (AE) and shall have a Minimum Compressive Strength (f'_c) of 5000 psi at 28 days. Compressive Strength at transfer of the Prestressing Force shall be not less than 4000 psi. Concrete in Build - Ups shall have a minimum Compressive Strength (f'_c) of 4000 psi.

Prestressing Reinforcement : Seven wire stress relieved or low relaxation strands shall conform to the general requirements of ASHTO M203. Broken wires within individual strands will be permitted up to 2% of the total number of wires in each pile, providing that there is not more than one broken wire per strand. Two or more broken wires per strand will be cause for replacement of the strand, even though the two broken wires are within the 2% limitation.

Build-Ups : To provide for Build-Ups of Piles where authorized by the Engineer, concrete shall be cut back to expose the strands for a distance sufficient to provide a lap of 60 diameter of the reinforcing bars required for Build-Up. Reinforcing of Build-Ups shall have a minimum area equal to 1/2% of the gross section of pile. Placement of bars shall be in a symmetrical pattern of not less than four bars. See Section 805.1(b) of the Standard Specifications.

Forms : For forming exterior of piles, the use of steel forms on concrete founded casting beds is required, unless otherwise approved by the Engineer. Side forms may have a maximum drift on each side not exceeding 1/4" per foot. Tolerances : Pile ends shall be plane surfaces and perpendicular to axis of pile with a maximum tolerance of 1/8" per foot transversely.

PRECAST PILE REINFORCING

Pile Size	No. Req'd.	Bar Size
6" Oct.	8	#7
8" Oct.	8	#7
6" Sq.	8	#7
8" Sq.	8	#8

PRECAST CONCRETE PILES

GENERAL NOTES
 The maximum sweep (deviation from straightness measured along two perpendicular faces of the pile, while not subject to bending forces) shall not exceed 1/8" in 10 ft. of its length.
 General : Shipment of piles from the plant site or pile driving will not be permitted until the required minimum compressive strength is reached, and in no case less than 10 days after pouring the concrete. Piles may be removed from casting bed to a nearby storage any time after transfer of stress.
 Spiral Reinforcing : Spiral reinforcing shall be steel wire meeting the requirements of ASHTO M32 or M225 with a minimum diameter of 0.3175" or shall be plain round steel bars meeting the requirements of ASHTO M31 or M53, GR. 60 with a minimum diameter of 0.3175".
 Manufacture, Transportation and Storage : See Section 802 "Concrete for Structures" of the Standard Specifications.

Unless otherwise approved by the Engineer, all protruding or exposed pile lifting or transporting devices above the finished ground shall be removed after pile driving is complete. Removal shall be a minimum of 1' below the surface of the pile and the cavity shall be filled with a non-shrink grout listed on the Department's QPL.
 Installation, Measurement and Payment : See Section 805 "Piling" of the Standard Specifications. Precast Prestressed Concrete Piling will be paid for at the contract unit price per Linear Foot bid for "Concrete Piling".
 The Contractor may elect to use a Precast Concrete Pile in lieu of the Prestressed Concrete Pile.
 All concrete shall be Class S (AE) and shall have a minimum compressive strength (f'_c) of 4000 psi at 28 days.
 All longitudinal reinforcing bars shall be deformed bars of ASHTO M31 or M53, Gr. 60.
 All spiral reinforcing shall be the same as that shown for prestressed concrete.

DETAILS OF STANDARD CONCRETE PILES FOR EARTHQUAKE REGION B

ROUTE 12383B, STD

ARIZONA STATE HIGHWAY COMMISSION

BRIDGE ENGINEER
 REGISTERED PROFESSIONAL ENGINEER
 No. 4537
 DATE: 04-10-2003
 DATE: 04-10-2003
 DATE: 04-10-2003
 DATE: 04-10-2003
 SCALE: 1" = 1'-0"
 DRAWING NO. 2383B

DATE REVISION	DATE FILLED	DATE REVISION	DATE FILLED	FED. PROJ. NO.	STATE	FED. AID PROJ. NO.	SHEET NO.	TOTAL SHEETS
04-10-2003	4-10-2003				6			
12-10-2009								

CONC. PILES 2383B



Added paragraph to General Notes
 Checked by: CJF Date: 12-10-2009
 Revised and redrawn MJT 04-10-2003
 Chk'd. By: CJF 04-10-2003