

SILICONE ADDITIVES FOR ASPHALT CEMENTPRODUCTSUPPLIER

Dow Corning 200 Fluid
(12,500 C.S.)

Dow Corning Corporation
Suite 209
6350 LBJ Freeway
Dallas, TX 72540
or
Dow Corning Corporation
Midland, Michigan 48640

General Electric Viscaseal
(12,500 C.S.)

General Electric Co.
Silicone Products Division
Waterfront, NY 12188

TBF 9-12, 500

Southwest Silicone Company, Inc.
(Division of Path Silicones)
P.O. Box 5723
Arlington, Texas 76005

Union Carbide L-45/12500

Union Carbide Corp.
Specialty Chemicals Div.
39 Old Ridgebury Rd.
Danbury, CT 06817-0001

METHOD OF DOCUMENTATION OF ACCEPTANCE: By brand and manufacturer.

Requirements for acquiring approval to be added to QPL: Qualification is based upon the submittal of physical and chemical properties and a sample by the manufacturer to the Materials Division. Inclusion in the Qualified Products List will be dependent upon the review of material properties and the outcome of testing of the sample.

RECOMMENDED USAGE RATE:

Mix 500 mL (1 pint) silicone fluid in 15 L (4 gal) of diesel fuel. Add 250 mL (½ pint) of this mixture to each 3800 L (1000 gal) of asphalt cement.